

TECHNICAL DATASHEET

GS TPO RF BG S

TPO MEMBRANE FLEECE BACKED

GreenShield™ TPO RF BG (S) Membrane is a high performance, heat weldable, single side fleece backed thermoplastic polyolefin (TPO) sheet, manufactured and supplied in thickness of 1.2 and 1.5 mm, designed for waterproofing and heat shielding roofs of new and existing buildings. The membrane is designed for adhesion to screed, PCC, RCC, cementitious and other adhesives for easy application over flat roofs.

Based on advanced polymer chemistry, the membrane has excellent weather resistance and fire protection, sustaining cycles of hot, cold, wet and dry environmental conditions, remaining flexible over years, maintaining its integrity and continuing to provide protection from water seepage and heat.

High mechanical properties of the membrane ensure superior puncture resistance, breaking and tearing strength, while enabling excellent heat weld for fusion along the edges.

GS membranes are designed with high solar reflective index, thermal emittance, and solar reflectance, enabling the membrane to provide insulation with high surface albedo.



Features & Benefits

- ◇ Supplied in pre-manufactured standard thickness. No thickness variation unlike liquid applied systems.
- ◇ Outstanding puncture resistance, high breaking and tearing strength, with very high peel strength of seam joints and heat welds
- ◇ Chlorine free, plasticizer free, phthalate free. Environmentally friendly and safe for humans
- ◇ Exceptional resistance to heat, UV, Ozone, bacteria, chemical, acid corrosion
- ◇ Resistance to root penetration, suitable for green roofs and below ground applications.
- ◇ Continuous serviceability from -30°C to 100°C - without cracking, tearing or brittleness failure

Application Areas

- ◇ Flat Roofs
 - ◇ Residential Buildings & Homes
 - ◇ Commercial Office Buildings
 - ◇ Malls, Hospitals, Schools
- ◇ Green Roofs, Podiums & Balconies

Packing, Storage & Coverage

ROLL DETAILS	Thickness (mm)	1.2	1.2	1.5	1.5
	Width (mtr)	1.6	2.0	1.6	2.0
	Length (mtr)	20	20	20	20
	Sq.mts (mtr ²)	32	40	32	40
	Weight (kgs)	38	48	47	58
STORAGE	Store membranes in dry and clean conditions and in their original, closed wrapping away from sources of chemical contamination, damage, ignition sources and open flame. Shelf life is beyond 5 years. Exercise caution when lifting, moving, transporting, storage and handling to avoid puncture and physical damage.				
COVERAGE	The dimensions of the membrane are calculated to cover the substrate, including seam overlaps. Standard Seams: 75 mm Seams with mechanical anchoring: 150 mm Upstands: additional length of 150 mm				



GreenShield

Heatshielding & Waterproofing Your Roof

PRODUCT OF ZYLOG ELASTOCOMP
Zylog House | Lane 4
Kalyaninagar | Pune 411006
+91 77588 65314 | sales@greenshield.co.in

PROPERTY	GS TPO 1.2 RF BG S	GS TPO 1.5 RF BG S
Nominal Thickness mm; ASTM D751	1.2 ± 10%	1.5 ± 10%
Typical Weight Kg/m ²	1.18 ± 10%	1.45 ± 10%
Breaking Strength LBF; MD/TD; ASTM D 751 Grab Method	100 Min 125 Typical	110 Min 130 Typical
Elongation at Break %, MD/TD; ASTM D 751	60 Min 80 Typical	60 Min 80 Typical
Tearing Strength LBF; MD/TD; ASTM D 751 Procedure B	25 Min 30 Typical	25 Min 30 Typical
Brittleness Point °C; ASTM D 2137	-40°C	-40°C
Linear Dimensional Change %; 6hrs @ 70°C; ASTM D 1204	< 1%	< 1%
Ozone Resistance 100 pphm, 168 hrs; ASTM D 1149	Pass	Pass
Water Absorption %; 66 hrs @ 70°C TOP; ASTM D471	< 3.0%	< 3.0%
Factory Seam Strength LBF; ASTM D 751 Grab Method	66 Min 80 Typical	66 Min 80 Typical
Water Vapour Permeance Perms; ASTM E96, Procedure B	0.10 Max	0.10 Max
Puncture Resistance LBF; ASTM D751	57	70
Properties after Heat Ageing 32weeks @ 115°C; ASTM D 573 (i) Breaking Strength (LBF) (ii) Elongation Retention (%) iii) Weight change (%) (iv) Tearing Strength (LBF)	Retention 90% Min 90% Min ± 1.0 Max 60% Min	Retention 90% Min 90% Min ± 1.0 Max 60% Min
Weather Resistance KJ/(m ² .mm); ASTM G155	> 21,600	> 21,600
Field Seam Strength LBF; ASTM D 751 Grab Method	40 Min 60 Typical	40 Min 60 Typical
Solar Reflectance Index	100	100
Reflectivity ASTM C1549	0.79	0.79
Emissivity ASTM C1371	0.909	0.909

Fire-resistant version, meeting EN 13501-1 and 13501-5 is also available. Contact us for further information.

Note & Disclaimer: For latest updates and additional info, please consult our website at www.greenshield.co.in. Testing results and/or copies of Approval Documents for above mentioned membranes are available on request.

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is user responsibility to ensure that product is used and handled correctly and in accordance with applicable standards and recommendations and only for the intended purpose. We reserve the right to update information without prior notice to reflect ongoing research and development program. Country specific recommendations, considering local standards, practice codes, building regulations and industry guidelines, may effect installation recommendations. The supply of our products and services is subject to terms, warranties and exclusions available to you on request.